

## WHAT IS CLAIMED IS:

1. A method for manufacturing a semiconductor device, said method comprising the steps of:

5 forming an insulating film on a semiconductor base material, said insulating film being predominantly composed of organic siloxane and containing an organic component which has no chemical bond to said organic siloxane; and

10 applying plasma treatment to said insulating film to remove said organic component and form a modifying layer on a surface of said insulating film.

2. The method for manufacturing a semiconductor device according to claim 1, wherein said insulating film forming step  
15 is performed by a chemical vapor deposition method.

3. The method for manufacturing a semiconductor device according to claim 1, wherein said insulating film forming step includes steps of:

20 coating said semiconductor base material with an insulating film composition containing said organic siloxane and said organic component; and

25 heat treating said insulating film composition at a temperature between 100°C and 200°C.

4. The method for manufacturing a semiconductor device according to claim 1, wherein said plasma treatment is performed using a gas containing at least one selected from the group consisting of oxygen, hydrogen and nitrogen.

30 5. The method for manufacturing a semiconductor device according to claim 1, wherein molecules of said organic siloxane

contain an alkyl group or an allyl group.

6. The method for manufacturing a semiconductor device according to claim 5, wherein said organic siloxane is MSQ.

5

7. The method for manufacturing a semiconductor device according to claim 1, further comprising a step of:

after said plasma treatment, heat treating said insulating film at a temperature between 250°C and 450°C.

10

8. The method for manufacturing a semiconductor device according to claim 1, further comprising a step of:

after said plasma treatment, heat treating said insulating film at a temperature between 400°C and 450°C.

15

9. A method for manufacturing a semiconductor device, said method comprising the steps of:

forming an insulating film on a semiconductor base material, said insulating film being composed of organic siloxane; and

20

applying plasma treatment to said insulating film to remove an organic group from said organic siloxane and form a modifying layer on a surface of said insulating film.

25

10. The method for manufacturing a semiconductor device according to claim 9, wherein said insulating film forming step is performed by a chemical vapor deposition method.

11. The method for manufacturing a semiconductor device according to claim 9, wherein said insulating film forming step includes steps of:

30

coating said semiconductor base material with an

insulating film composition containing said organic siloxane and said organic component; and

heat treating said insulating film composition at a temperature between 100°C and 200°C.

5

12. The method for manufacturing a semiconductor device according to claim 9, wherein said plasma treatment is performed using a gas containing at least one selected from the group consisting of oxygen, hydrogen and nitrogen.

10

13. The method for manufacturing a semiconductor device according to claim 9, wherein molecules of said organic siloxane contain an alkyl group or an allyl group.

15

14. The method for manufacturing a semiconductor device according to claim 13, wherein said organic siloxane is a phenyl methyl siloxane.

15. The method for manufacturing a semiconductor device according to claim 9, further comprising a step of:

after said plasma treatment, heat treating said insulating film at a temperature between 250°C and 450°C.

16. The method for manufacturing a semiconductor device according to claim 9, further comprising a step of:

after said plasma treatment, heat treating said insulating film at a temperature between 400°C and 450°C.